

2810 Clark Avenue • St. Louis, MO 63103-2574 • (314) 531-8080 • FAX (314) 531-8085

Chemical, Metallurgical, Mechanical, Nondestructive, Environmental Testing, Analyses and Field Service.

EARTH CONTACT PRODUCTS LLC

15612 S. Keeler Terrace
Olathe, KS 66062

September 5, 2012

Lab No. 12P-4802

P.O. No. Verbal Brandon

Page 1 of 1

Attention: **Brandon Walter**

REPORT OF MECHANICAL TESTS


SAMPLE: 8 Each Tube Samples Submitted 9-4-2012


SUBJECT: Full Size Compression Load Test (Per Client's Instructions)

TEST PROCEDURE: Test was performed using a SATEC Universal Tester, S/N 1269.

SAMPLE ID	COMPRESSION LOAD @ YIELD (LBS)	COMPRESSION LOAD @ PEAK (LBS)
A-2 7/8 -1	75000	79110
A-2 7/8 -2	75500	79570
L-2 7/8 -1	74000	77510
L-2 7/8 -2	76000	78860
A-3 ½ -1	85500	93770
A-3 ½ -2	86000	94670
L-3 ½ -1	81000	84590
L-3 ½ -2	82000	85600

Identification of tested specimen provided by the client.




Karl Schmitz, Director
Materials Testing

